

## OK Tubrod 15.14

OK Tubrod 15.14 is a flux-cored, tubular wire for all-positional welding using either Ar/CO<sub>2</sub> or CO<sub>2</sub>. The wire is suitable for all mild and medium tensile structural steels. The running characteristics are exceptional, using the spray mode of transfer, and this applies equally to both shielding gases. OK Tubrod 15.14 is also universally approved to grade 3 by all major authorities. Shielding gas Ar/20%CO<sub>2</sub> or CO<sub>2</sub>.

<b>Classifications Weld Metal</b>	SFA/AWS A5.36: E71T1-C1A0-CS2-H8 SFA/AWS A5.36: E71T1-M21A0-CS2-H8 EN ISO 17632-A: T 46 2 P C1 1 H5 EN ISO 17632-A: T 46 2 P M21 2 H5
<b>Godkännanden</b>	ABS 3YSA H5 (C1 & M21) BV SA3YM (C1) CE EN 13479 DB 42.039.05 (M21 and C1) DNV III YMS H5 (C1) DNV-GL III YMS (M21) LR 3YS H5 (C1 & M21) LR 3YS H5 (M21)* NAKS/HAKC 1.2 mm PRS 3YS H10 (C1 & M21) RIINA 2Y S H5 (C1) RS 3YMS H5 (C1) RS 3YSH5 (C1 & M21) VdTÜV 07651

Godkännanden baseras på fabriken lokaliserings. Vänligen kontakta ESAB för mer information.

<b>Welding Current</b>	DC+
<b>Diffusible Hydrogen</b>	< 5 ml/100g
<b>Alloy Type</b>	C Mn

### Typical Tensile Properties

Condition	Yield Strength	Tensile Strength	Elongation
<b>C1 shielding gas</b>			
As Welded	497 MPa	588 MPa	27 %

### Slagseghetsdata Charpy V

Condition	Testing Temperature	Impact Value
<b>C1 shielding gas</b>		
As Welded	-20 °C	110 J

### Svetsgodsanalys

C	Mn	Si
<b>C1 Shielding gas</b>		
0.05	1.30	0.54

### Insmätningsdata

Diameter	Ampere	Volt	Trådmatningshastighet	Insmätningshastighet
1.2 mm	110-300 A	21-32 V	3.2-14.5 m/min	1.3-5.8 kg/h
1.4 mm	130-320 A	22-32 V	3.0-12.5 m/min	1.4-6.3 kg/h
1.6 mm	150-360 A	24-34 V	3.0-11.0 m/min	2.0-6.2 kg/h